



| Glass composition | Step 1 time (min) | Step 2 heating (min) | Step 3 temperature (C°) | Step 3 Time (min) | Step 4 heating (min) | Step 5 temperature (C°) | Step 5 Time (min) |
|-------------------|-------------------|----------------------|--------------------------|-------------------|----------------------|-------------------------|-------------------|
| 33,1 | 5 min | 20 min | 85 C° | 25 min | 12 min | 125 C° | 45 min |
| 44,2 | 10 min | 22 min | 90 C° | 30 min | 12 min | 130 C° | 50 min |
| 55,2 | 10 min | 22 min | 90 C° | 35 min | 12 min | 132 C° | 55 min |
| 66,2 | 10 min | 22 min | 90 C° | 40 min | 12 min | 132 C° | 60 min |
| 88,2 | 15 min | 32 min | 90 C° | 45 min | 17 min | 132 C° | 65 min |
| 10,10,2 | 15 min | 40 min | 90 C° | 50 min | 23 min | 135 C° | 75 min |
| 12,12,2 | 15 min | 40 min | 90 C° | 60 min | 23 min | 135 C° | 85 min |

For every additional EVA layer of 0.4 mm second hold temperature (step 5) must be increased of 5 min.